

Site-selective oxygen isotope effect on the magnetic field penetration depth in underdoped $\text{Y}_{0.6}\text{Pr}_{0.4}\text{Ba}_2\text{Cu}_3\text{O}_{7-\delta}$

R. Khasanov,^{1,2,*} A. Shengelaya,¹ E. Morenzoni,² M. Angst,¹ K. Conder,³
I. M. Savić,⁴ D. Lampakis,⁵ E. Liarakis,⁵ A. Tatsi,⁵ and H. Keller¹

¹*Physik-Institut der Universität Zürich, Winterthurerstrasse 190, CH-8057, Switzerland*

²*Laboratory for Muon Spin Spectroscopy, Paul Scherrer Institut, CH-5232 Villigen PSI, Switzerland*

³*Laboratory for Neutron Scattering, ETH Zürich and Paul Scherrer Institut, CH-5232 Villigen PSI, Switzerland*

⁴*Faculty of Physics, University of Belgrade, 11001 Belgrade, Serbia and Montenegro*

⁵*Department of Physics National Technical University Athens 157 80, Greece*

We report site-selective oxygen isotope ($^{16}\text{O}/^{18}\text{O}$) effect (OIE) measurements on the in-plane penetration depth λ_{ab} in underdoped $\text{Y}_{0.6}\text{Pr}_{0.4}\text{Ba}_2\text{Cu}_3\text{O}_{7-\delta}$, using the muon-spin rotation (μSR) technique. A pronounced OIE on the transition temperature T_c as well as on $\lambda_{ab}^{-2}(0)$ was observed, which mainly arises from the oxygen sites within the superconducting CuO_2 planes (100 % within error bar). The values of the corresponding relative isotope shifts were found to be $T_c/T_c = -3.7(4) \%$ and $\Delta\lambda_{ab}^{-2}(0)/\lambda_{ab}^{-2}(0) = -6.2(1.0)\%$. Our results imply that in this compound the phonon modes involving the movement of planar oxygen are dominantly coupled to the electrons.

PACS numbers: 76.75.+i, 74.72.-h, 82.20.Tr, 74.25.Kc

More than 15 years after the discovery of the cuprate high T_c superconductors (HTSC), their pairing mechanism is still not understood. For a long time, a role of phonons in this mechanism was dismissed, despite evidence of their relevance, for example by isotope experiments (see, e.g., Refs. 1,2,3,4,5,6). One of the reasons for this was the prevailing belief that phonons simply could not account for such high transition temperatures (T_c). The recent discovery of MgB_2 ,⁷ where phonons are clearly the pairing glue leading to an unexpectedly high $T_c \approx 40$ K, clearly falsified this belief. Many other widely cited reasons as to why phonons ought to play no role in HTSC also do not stand to scrutiny.^{8,9} Recent work by inelastic neutron scattering (INS)^{10,11} and angle resolved photoemission spectroscopy (ARPES)^{12,13} gave good indications of a strong electron-phonon coupling in various HTSC, invigorating the debate about the relevance of phonons.^{14,15}

For conventional superconductors (including doped fullerenes¹⁶ and MgB_2 ¹⁷), key experimental evidence for a phonon mediated pairing was provided by measurements of the isotope effect (IE) on T_c . In complex materials, such as the HTSC, T_c may depend on many parameters in a non-trivial way. Important complimentary information can be obtained from the IE on the magnetic penetration depth λ . Previous studies^{3,4,5,6} showed substantial oxygen isotope ($^{16}\text{O}/^{18}\text{O}$) effect (OIE) on the in-plane penetration depth λ_{ab} , which indicates an unusual (e.g., non-adiabatic) coupling of the electrons to phonon modes involving the movement of the isotope substituted atoms. It is important to identify the relevant phonon modes responsible for this effect. Keen insight in this respect can be obtained from studying the site-selective oxygen isotope effect (SOIE), as we will detail below. While two reliable reports on the SOIE on T_c exist,^{2,18} the SOIE on λ_{ab} was previously deduced only in a very indirect way from magnetization measurements in the vicinity of T_c .¹⁸

In this communication, we report on the SOIE on T_c and on λ_{ab} in underdoped $\text{Y}_{0.6}\text{Pr}_{0.4}\text{Ba}_2\text{Cu}_3\text{O}_{7-\delta}$, measured directly and accurately by using the transverse field muon spin rotation (TF- μSR) technique.¹⁹ The result clearly indicates a strong coupling of the electronic subsystem to phonon modes involving movements of the oxygen atoms in the CuO_2 plane, while suggesting that modes involving apical and chain oxygen are less strongly coupled to the electrons. This agrees with the conclusions observed from the combination of INS^{10,11} and ARPES^{12,13} results, which were obtained in a completely different way and in other HTSC.

Polycrystalline samples of $\text{Y}_{0.6}\text{Pr}_{0.4}\text{Ba}_2\text{Cu}_3\text{O}_{7-\delta}$ were prepared by standard solid state reaction.²⁰ In order to prepare oxygen site-selective samples a two-step exchange process was applied.^{2,20} In the first step [500°C, 35 h at 1.2 bar in $^{16}\text{O}_2$ ($^{18}\text{O}_2$) gas] two pairs of completely oxygen substituted samples ($^{16}\text{O}_{\text{pac}}$ and $^{18}\text{O}_{\text{pac}}$) were prepared [here indexes p , a and c mean planar (within CuO_2 planes), apical and chain oxygen, respectively]. In the second step (330°C, 150 h, 1.2 bar) two site-selective oxygen samples ($^{16}\text{O}_p$ $^{18}\text{O}_{\text{ac}}$ and $^{18}\text{O}_p$ $^{16}\text{O}_{\text{ac}}$) were prepared via annealing one $^{16}\text{O}_{\text{pac}}$ sample in a $^{18}\text{O}_2$ atmosphere and one $^{18}\text{O}_{\text{pac}}$ sample in $^{16}\text{O}_2$ gas. The other two samples (one $^{16}\text{O}_{\text{pac}}$ and one $^{18}\text{O}_{\text{pac}}$) were simultaneously annealed in the same atmosphere as before. For the totally exchanged sample ($^{18}\text{O}_{\text{pac}}$) the ^{18}O content, estimated from the change of the sample weight after annealing, was found to be 90(2) %. The oxygen-tracer diffusion calculation²⁰ for the material used in this work (average measured grain size is 16 μm) shows that after annealing at 330°C, during 150 h more than 90 % of the apex+chain sites and only about 10-15 % of the plane sites should be exchanged. Keeping in mind that there are 4 planar and 3 apical and chain oxygen sites in the unit cell of $\text{Y}_{0.6}\text{Pr}_{0.4}\text{Ba}_2\text{Cu}_3\text{O}_7$, for the above mentioned annealing procedure, one would expect about 45 % of an

average oxygen substitution. The experimental estimate (from the change of the sample weight) gives 41(2) % for both site-selective samples, in good agreement with the theoretical calculation.




FIG. 1: Room-temperature Raman spectra of the $\text{Y}_{0.6}\text{Pr}_{0.4}\text{Ba}_2\text{Cu}_3\text{O}_{7-\delta}$ samples. For xx polarization the line corresponds to the out-of-phase motion of the planar oxygen atoms (^{16}O , 325 cm^{-1} ; ^{18}O , 294 cm^{-1}). For zz polarization the two lines correspond to the in-phase motion of the CuO_2 plane oxygen (^{16}O , 436 cm^{-1} ; ^{18}O , 415 cm^{-1}) and to the bond-stretching mode of the apical oxygen (^{16}O , 512 cm^{-1} ; ^{18}O , 482 cm^{-1}).

The site-selectivity of the oxygen exchange was then checked by Raman spectroscopy. The 488 nm and 514.5 nm lines of an Ar laser were used for excitation. Figure 1 shows Raman spectra of all samples with zz and xx polarizations. In the zz polarization for the $^{16}\text{O}_{\text{pac}}$ sample we observe two lines, one corresponding to the in-phase motion along the c -axis of the planar oxygen atoms (436 cm^{-1}) and one corresponding to the bond-stretching mode of apical oxygen, which in this compound is located at 512 cm^{-1} .²¹ In the xx polarization a line at 325 cm^{-1} is seen, corresponding to the out-of-phase vibrations of the planar oxygen atoms.²¹ In the $^{18}\text{O}_{\text{pac}}$ sample, the Raman lines are all shifted to lower frequencies with amounts agreeing well with the ones obtained in Ref. 2, indicating a nearly complete exchange of ^{16}O with ^{18}O . In the site-selective sample $^{16}\text{O}_{\text{p}}^{18}\text{O}_{\text{ac}}$, only the position of the apical oxygen line is shifted to the lower frequency, whereas the lines corresponding to the plane oxygen stay the same [apart from a small shift of one Raman line




FIG. 2: Section near T_c of the normalized (to the value at 5 K) magnetization curves (1 mT, FC) of the site-selective $\text{Y}_{0.6}\text{Pr}_{0.4}\text{Ba}_2\text{Cu}_3\text{O}_{7-\delta}$ samples.

(433 cm^{-1} instead of 436 cm^{-1}), probably due to a small unintentional partial substitution by ^{18}O]. Note that the apical line (492 cm^{-1}) is also slightly shifted from the expected 482 cm^{-1} , indicating that oxygen exchange for the apical and chain oxygen is slightly incomplete. In the $^{18}\text{O}_{\text{p}}^{16}\text{O}_{\text{ac}}$ sample only two planar lines are shifted, while the apical line stays the same. Therefore, the Raman results confirm the almost complete site-selective oxygen substitution in all samples.

To determine the site-selective oxygen isotope shift on T_c , low field [1mT, field cooled (FC)] SQUID magnetization (M) measurements were performed. Figure 2 shows the $M(T)$ dependencies in the vicinity of T_c for all four samples. It can be seen that the $^{16}\text{O}_{\text{pac}}$ sample has a higher T_c than the $^{18}\text{O}_{\text{pac}}$ one with nearly the same transition width. The isotope shift $\Delta T_c = -1.66(17)\text{ K}$ for completely substituted samples ($^{16}\text{O}_{\text{pac}}$ and $^{18}\text{O}_{\text{pac}}$) is in agreement with previous results^{5,22} (T_c was extracted from the intercept of the linear extrapolation as shown in Fig. 2). The data points of the site-selective $^{16}\text{O}_{\text{p}}^{18}\text{O}_{\text{ac}}$ sample coincide within error with those of the $^{16}\text{O}_{\text{pac}}$ sample, whereas the $^{18}\text{O}_{\text{p}}^{16}\text{O}_{\text{ac}}$ data points coincide with the $^{18}\text{O}_{\text{pac}}$ ones, indicating that the OIE on T_c is related to the oxygen within the CuO_2 planes. The results of the SOIE on T_c are summarized in Table I. The OIE exponent on T_c was determined as $\alpha_{\text{O}} = -d \ln T_c / d \ln M_{\text{O}}$ (M_{O} is the mass of the oxygen isotope).

In order to determine the SOIE on λ_{ab} we performed TF- μSR measurements at the Paul Scherrer Institute (PSI), Switzerland, using the πM3 beam line. The samples were cooled from far above T_c in a magnetic field of 200 mT. In a powder sample the magnetic penetration depth λ can be extracted from the muon-spin depolarization rate $\sigma(T) \propto 1/\lambda^2(T)$, which probes the second




FIG. 3: (a) Temperature dependence of the depolarization rate σ_{sc} in site-selective $\text{Y}_{0.6}\text{Pr}_{0.4}\text{Ba}_2\text{Cu}_3\text{O}_{7-\delta}$ samples (200 mT, FC). Data points below 10 K are not shown (see text for an explanation). The solid lines correspond to fits to the power law $\sigma_{sc}(T)/\sigma_{sc}(0) = 1 - (T/T_c)^n$ for the $^{16}\text{O}_{\text{pac}}$ and $^{18}\text{O}_{\text{pac}}$ samples. (b) Same as in (a), but after subtracting the fitted curve for the $^{16}\text{O}_{\text{pac}}$ sample.

moment $\langle \Delta B^2 \rangle^{1/2}$ of the probability distribution of the local magnetic field function $p(B)$ in the mixed state.¹⁹ For highly anisotropic layered superconductors (like the cuprate superconductors) λ is mainly determined by the in-plane penetration depth λ_{ab} : $\sigma(T) \propto 1/\lambda_{ab}^2(T)$.¹⁹ The depolarization rate σ was extracted from the μSR time spectra using a Gaussian relaxation function $R(t) = \exp[-\sigma^2 t^2/2]$. As discussed in Ref. 5, the measured total depolarization rate σ is determined by three terms: a superconducting (σ_{sc}), an antiferromagnetic (σ_{afm}), and a small nuclear magnetic dipole (σ_{nm}) contribution. The antiferromagnetic contribution σ_{afm} is present *only* at low temperatures. Therefore data points below 10 K were excluded in the analysis. The dipole contribution σ_{nm} is practically temperature independent below 100 K, and σ_{sc} was determined by subtracting σ_{nm} measured above T_c from σ according to: $\sigma_{sc} = \sqrt{\sigma^2 - \sigma_{nm}^2}$. Figure 3 shows the temperature dependence of σ_{sc} for the $\text{Y}_{0.6}\text{Pr}_{0.4}\text{Ba}_2\text{Cu}_3\text{O}_{7-\delta}$ site-selective samples. It is evident that a remarkable oxygen isotope shift of T_c as well as of σ_{sc} is present. More importantly, the data points of the site-selective $^{16}\text{O}_{\text{p}}^{18}\text{O}_{\text{ac}}$ ($^{18}\text{O}_{\text{p}}^{16}\text{O}_{\text{ac}}$) samples coincide with those of the $^{16}\text{O}_{\text{pac}}$ ($^{18}\text{O}_{\text{pac}}$) samples. In order to put

into evidence these results, the curve fitting the temperature dependence of $\sigma_{sc}(T)$ for $^{16}\text{O}_{\text{pac}}$ (shown below) was subtracted from the experimental data [Fig. 3(b)]. It can be seen that the experimental points for the two pairs of samples mentioned above coincide within the error bars (nearly within the error bars in the case of $^{16}\text{O}_{\text{pac}}$ and $^{16}\text{O}_{\text{p}}^{18}\text{O}_{\text{ac}}$). The data in Fig. 3 were fitted to the power law $\sigma_{sc}(T)/\sigma_{sc}(0) = 1 - (T/T_c)^n$ with $\sigma_{sc}(0)$ as a free parameter.¹⁹ The value of T_c was taken from the magnetization measurements (see Table I), n was fitted as a common parameter for all four data sets and was found to be $n = 1.87(4)$, which is typical for underdoped YBCO.¹⁹ Note, that the exponent n is isotope independent^{4,5} and that fits with the same n for all data sets allow to increase the accuracy in the determination of $\sigma_{sc}(0)$. The values of $\sigma_{sc}(0)$ obtained from the fits are listed in Table I and are in agreement with previous results.^{5,23} From the values of $\sigma_{sc}(0)$ the relative isotope shift of the in-plane penetration depth $\Delta\lambda_{ab}^{-2}(0)/\lambda_{ab}^{-2}(0) = [\sigma_{sc}(X)(0) - \sigma_{sc}(^{16}\text{O}_{\text{pac}})(0)]/\sigma_{sc}(^{16}\text{O}_{\text{pac}})(0)$ and the OIE exponent $\beta_O = -d \ln \lambda_{ab}^{-2}(0)/d \ln M_O$ were determined (see Table I). Here X denotes $^{16}\text{O}_{\text{p}}^{18}\text{O}_{\text{ac}}$, $^{18}\text{O}_{\text{p}}^{16}\text{O}_{\text{ac}}$, and $^{18}\text{O}_{\text{pac}}$. Our results (summarized in Table I) are in good agreement with previous estimates of SOIE from magnetization experiments¹⁸ and our previous μSR non site-selective OIE results.⁵




FIG. 4: Plot of the OIE exponent β_O ($-\Delta\lambda_{ab}^{-2}(0)/\lambda_{ab}^{-2}(0)$) versus the OIE exponent α_O ($-\Delta T_c/T_c$) for site-selective $\text{Y}_{0.6}\text{Pr}_{0.4}\text{Ba}_2\text{Cu}_3\text{O}_{7-\delta}$ samples. The error bars of the “trivial” $^{16}\text{O}_{\text{pac}}$ point (zero isotope shift by definition) indicate the intrinsic uncertainty of the experimental procedures on the estimation of T_c and λ_{ab} .

In Fig. 4, we plot the OIE exponent β_O ($-\Delta\lambda_{ab}^{-2}(0)/\lambda_{ab}^{-2}(0)$) vs the OIE exponent α_O ($-\Delta T_c/T_c$), in analogy with Ref. 5. Substantial OIE on T_c and $\lambda_{ab}^{-2}(0)$

TABLE I: Summary of the SOIE on T_c and $\lambda_{ab}^{-2}(0)$ for $Y_{0.6}Pr_{0.4}Ba_2Cu_3O_{7-\delta}$ extracted from the experimental data (see text for an explanation). The values of $\Delta T_c/T_c$, α_O , $\Delta\lambda_{ab}^{-2}(0)/\lambda_{ab}^{-2}(0)$, and β_O are not corrected for the incomplete oxygen-isotope exchange (see text).

Sample	T_c (K)	ΔT_c (K)	$\frac{\Delta T_c}{T_c}$ (%)	α_O	$\sigma_{sc}(0)$ (μs^{-1})	$\Delta\sigma_{sc}(0)$ (μs^{-1})	$\frac{\Delta\lambda_{ab}^{-2}(0)}{\lambda_{ab}^{-2}(0)}$ (%)	β_O
$^{16}O_{pac}$	44.62(12)	—	—	—	1.090(7)	—	—	—
$^{16}O_p^{18}O_{ac}$	44.66(10)	0.04(16)	0.09(36)	-0.007(29)	1.070(9)	-0.020(11)	-1.8(1.0)	0.14(8)
$^{18}O_{pac}$	42.96(12)	-1.66(17)	-3.72(40)	0.298(32)	1.022(9)	-0.068(11)	-6.2(1.0)	0.50(8)
$^{18}O_p^{16}O_{ac}$	43.17(11)	-1.45(16)	-3.25(36)	0.260(29)	1.018(7)	-0.072(10)	-6.6(0.9)	0.53(7)

are observed for the completely ^{18}O substituted ($^{18}O_{pac}$) and the site selective $^{18}O_p^{16}O_{ac}$ samples, which are the same within error bars. The other site-selective sample ($^{16}O_p^{18}O_{ac}$) shows zero (within error bar) OIE on T_c and a very small, but possibly non zero, OIE on $\lambda_{ab}^{-2}(0)$. This effect very likely arises from the small fraction of ^{18}O that substituted ^{16}O oxygen within the CuO_2 planes, as seen in the Raman data (see Fig. 1). However, within the error bars, the OIE on $\lambda_{ab}^{-2}(0)$ can still be considered the same for the $^{16}O_{pac}$ and $^{16}O_p^{18}O_{ac}$ samples.

In summary, we performed μSR measurements of the site-selective oxygen isotope effect on the in-plane magnetic field penetration depth in underdoped polycrystalline $Y_{0.6}Pr_{0.4}Ba_2Cu_3O_{7-\delta}$ samples. It was found that the whole or nearly the whole effect on the transition temperature T_c and on the in-plane magnetic penetration depth λ_{ab}^{-2} (about 100 % within error bars) comes from the oxygen *within the superconducting CuO_2 planes* and not from the apical and chain oxygen. Noting that

the lattice parameters remain essentially unaffected by the isotope substitution,^{24,25} our results show the existence of a strong coupling of the electronic subsystem to phonon modes involving movements of the oxygen atoms in the CuO_2 plane, while suggesting that modes involving apical and chain oxygen are less strongly coupled to the electrons. This is in agreement with recent inelastic neutron scattering^{10,11} and photoemission^{12,13} studies, indicating a strong interaction between charge carriers and Cu-O bond-stretching-type of phonons.

This work was partly performed at the Swiss Muon Source (μS), Paul Scherrer Institute (PSI, Switzerland). The authors are grateful to A. Amato and D. Herlach for help during the μSR measurements, D. Di Castro for helpful discussions, and L. Meier for the measurements of the grain size distribution. This work was supported by the Swiss National Science Foundation and by the NCCR program MaNEP sponsored by the Swiss National Science Foundation.

* Electronic address: rustem.khasanov@psi.ch

¹ For a review, see J.P. Franck, in *Physical Properties High Temperature Superconductors IV*, edited by D.M Ginsberg (World Scientific, Singapore, 1994), pp. 189-293.

² D. Zech *et al.*, Nature **371**, 681 (1994).

³ G. M. Zhao *et al.*, Nature **385**, 236 (1997).

⁴ J. Hofer *et al.*, Phys. Rev. Lett. **84**, 4192 (2000).

⁵ R. Khasanov *et al.*, J. Phys.: Condens Matter **15**, L17 (2003).

⁶ R. Khasanov *et al.*, cond-mat/0305477.

⁷ J. Nagamatsu *et al.*, Nature **410**, 63 (2001).

⁸ P. B. Allen, Nature **412**, 494 (2001).

⁹ M. L. Kucic, Phys. Rep. **338**, 1 (2000).

¹⁰ R. J. McQueeney *et al.*, Phys. Rev. Lett. **82**, 628 (1999); **87**, 077001 (2001); M. d'Astuto *et al.*, *ibid.* **88**, 167002 (2002).

¹¹ J.-H. Chung *et al.*, Phys. Rev. B **67**, 014517 (2003).

¹² P. V. Bogdanov *et al.*, Phys. Rev. Lett. **85**, 2581 (2000); **89**, 167002 (2002).

¹³ A. Lanzara *et al.*, Nature **412**, 510 (2001).

¹⁴ M. Eschrig and M. R. Norman, Phys. Rev. B **67**, 144503 (2003); E. Schachinger, J. J. Tu, and J. P. Carbotte, *ibid.* **67**, 214508 (2003).

¹⁵ A. Bussmann-Holder *et al.*, J. Phys.: Condens. Matter **13**, L169 (2001); D. Mihailovic and V. V. Kabanov, Phys. Rev. B **63**, 054505 (2001); Z.-X. Shen *et al.*, Phil. Mag. B **82**, 1349 (2002); M. Tachiki, M. Machida, and T. Egami, Phys. Rev. B **67**, 174506 (2003).

¹⁶ A. P. Ramirez *et al.*, Phys. Rev. Lett. **68**, 1058 (1992).

¹⁷ S. L. Budko *et al.*, Phys. Rev. Lett. **86**, 1877 (2001); D. G. Hinks, H. Claus, and J. D. Jorgensen, Nature **411**, 457 (2001).

¹⁸ G.-M. Zhao, I. J. W. Ager, and D. E. Morris, Phys. Rev. B **54**, 14982 (1996).

¹⁹ P. Zimmermann *et al.*, Phys. Rev. B **52**, 541 (1995).

²⁰ K. Conder, Mater. Sci. Eng. **R32**, 41 (2001).

²¹ A. Gantis, M. Calamitoutou, D. Lampakis, A. Tatsi, and E. Liarokapis, in preparation.

²² J. P. Franck, J. Jung, and M. A.-K. Mohamed, Phys. Rev. B **44**, 5318 (1991).

²³ C. L. Seaman *et al.*, Phys. Rev. B **42**, 6801 (1990).

²⁴ K. Conder *et al.*, in *Phase Separation in Cuprate Superconductors*, edited by E. Sigmund and K. A. Müller (Springer, Berlin 1994) p. 210.

²⁵ F. Raffa *et al.*, Phys. Rev. Lett. **81**, 5912 (1998).